



EPIC™ SPARKLE GLITTERS

WILFLEX™ Epic Glitters are a non-phthalate special effect with a large-course glitter particles to bring a brilliant dazzle to print designs. The large glitter particles allow the base layer color to show through further enhancing the design possibilities and color combinations. Wilflex Silver and Gold Glitters are ready-for-use or can be tinted using Wilflex colorants for a custom look. Wilflex Glitters are low-cure special effects with excellent adhesion and wash durability.

HIGHLIGHTS

- ✔ SILVER GLITTER | 15330PFX
GOLD GLITTER | 89010PFX
YELLOW SPARKLE | 89010PFX
- ✔ Excellent adhesion to fabrics, stretch properties, and wash durability
- ✔ Brilliant glitter or sparkle effect to enhance graphics
- ✔ Low-cure, save energy
- ✔ Ready-for-use or tintable
- ✔ Use on light or dark grounds. Provides great contrast when printed on darks

PRINTING TIPS

- ✔ Stir inks before printing
- ✔ For best results, use recommended mesh counts and single print
- ✔ Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- ✔ Tintable with PC, Equalizer, RIO or MX finished ink colorants. See Pigment Loading section for suggested tinting percentages. Adjust the % colorant added based on the strength of the colorants and color saturation desired
- ✔ Print direct to fabric or over a flashed-dried base plate. Use a suitable underbase when printing on garments prone to bleed
- ✔ Print glitters in last position or flash after each print if using multiple screens
- ✔ Metallics reflect infrared heat and a forced air dryer is recommended for proper curing
- ✔ Curing is a time and temperature process, a lower oven temperature setting with a slower belt speed while maintaining recommended ink cure temperature is always best to protect fabric, control dye migration and reduce energy consumption
- ✔ Wilflex Glitters can be cured between 270°F - 320°F (132°C - 160°C)
- ✔ Can be mixed with other HD special effect bases or clears

COMPLIANCE

- ✔ Non-phthalate
- ✔ For individual compliance certifications and conformity statements, please visit: www.avient.com/wilflex-compliance

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications

PRODUCT INFORMATION BULLETIN



RECOMMENDED PARAMETERS

Fabric Types



100% cotton, blends, some synthetics

Mesh



Count: 24-38 t/in (9-15 t/cm) -
GLITTERS{}24-61 t/in (9-24 t/cm) -
YELLOW SPARKLE
Tension: 25-35 n/cm2

Squeegee



60/90/60, 60-70
Profile: Square, Sharp
Stroke: Hard flood, Medium stroke
Angle: 10-15%

Stencil



2 over 2
Off Contact: 1/16" (2mm)
Emulsion Over Mesh: 15-20%

Flash & Cure



Flash: 220°F (105°C)
Cure: 270°F (132°C)
Entire ink film

Pigment Loading



up to 3% PC recommended
up to 5% EQ recommended
up to 15% RIO recommended
up to 15% MX recommended

Wilflex™ Additives



Epic Curable Reducer < 10%
Epic Finesse < 10%
Epic Viscosity Buster - 1% max

Storage



65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt

Clean Up



Ink degradant or press wash

Health & Safety



Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR



AVIENT
SPECIALTY
INKS

V3.00 (Modified: 02/18/2021)

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.