



10099PFXATH EPIC™ ATHLETIC LB BASE

WILFLEX™ Epic Athletic LB Base is a non-phthalate, low-bleed plastisol ink with excellent opacity, brightness, and dye bleed resistance designed for printing on fabrics prone to dye migration, such as polyesters and poly/cotton blends

HIGHLIGHTS

- Mix with Wilflex™ PCs or EQualizers
- Good bleed resistance, reducing the need to underbase on polyesters
- Semi-opaque to opaque colors
- Good color fastness to crocking test

PRINTING TIPS

- Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- When blended according to formulations, colors will be semi-opaque to opaque
- Exhibits good color reproduction on white garment and over a base plate. For some colors, base mixing systems are limited in color saturation and may require an increased ink deposit or formula adjustment to achieve accurate color
- Use a printing technique to assure a good ink deposit to maximize bleed resistance and film strength properties
- Athletic LB Base is a low bleed mixing base. For challenging fabrics using sublimation dyes, a bleed blocking underbase such as EPIC ARMOR LC may be required
- Adjust flash cure temperature and dwell time so ink is just dry to touch. Depending on flash unit, a 2 - 3 second flash is adequate

COMPLIANCE

- Non-phthalate
- For individual compliance certifications and conformity statements, please visit: www.avient.com/wilflex-compliance

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications




AVIENT
SPECIALTY
INKS

V3.01 (Modified: 05/13/2022)

PRODUCT INFORMATION BULLETIN



RECOMMENDED PARAMETERS



Fabric Types

100% cotton, cotton blends, 100% polyester



Mesh

Count: 86-230 t/in (34-90 t/cm)
Tension: 25-35 n/cm2



Squeegee

Durometer: 60/90/60, 60-70
Profile: Square, Sharp
Stroke: Hard flood, Medium stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20%



Flash & Cure

Flash: 220°F (105°C)
Cure: 320°F (160°C)



Pigment Loading

EQ: Refer to IMS
PC: Refer to IMS
MX: N/A
RIO: N/A



Wilflex™ Additives

Epic Viscosity Buster-1% max



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Ink degradant or press wash



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.