









PLUE9040 EF HOT SPLIT ADDITIVE

PLUE9040 EF HOT SPLIT ADDITIVE can be added to Union Ultrasoft inks to improve hot split properties for printed heat transfers.


Highlights

-  Light and medium colored shirts.
-  Hot-split and cold-peel transfers.


Printing Tips

-  Ultrasoft inks will fully cure when the entire thickness of the ink deposit reaches 300°F (149°C).
-  Metallic inks are not recommended for transfer application.
-  Ultrasoft ink will semi-cure or gel when it reaches 240°F-250°F (115°C-121°C)
-  Add 5-10% by weight to Union Ultrasoft inks.











Compliance

-  Non-phthalate
-  Internationally compliant
-  Visit <https://www.avientspecialtyinks.com/services/compliance-support>

Precautions

-  The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications.

Recommended Parameters

 <p>Fabric Types Cotton</p>	 <p>Flash & Cure Flash: Pre-heat pallets Cure: 300°F</p>	 <p>Clean Up Unused ink will need to be disposed of responsibly. Standard plastisol cleaners, press wash, or ink degradant</p>
 <p>Mesh Count: 86-305 Tension: 18n-25n/cm3</p>	 <p>Pigment Loading N/A</p>	 <p>Health & Safety Find safety information here: www.avient.com/resources/safety-data-sheets or contact your local CSR</p>
 <p>Squeegee Durometer: 70, 80 Profile: Square Stroke: 1+ Angle: 15-20%</p>	 <p>Additives Do not use</p>	<p>2023, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.</p>
 <p>Stencil Standard Emulsion Off Contact: 1/16" (2mm) or greater Emulsion Over Mesh: 15-20%</p>	 <p>Storage 65 -95° F (18 -35° C) Avoid direct sunlight. Use within one year of receipt. Keep container well sealed.</p>	