LFP901 LFP-901 BLACK



LFP inks print well through a full range of meshes.

Highlights	Printing Tips
Versatile and ready to use.	 LFP inks print well through screen meshes in the range of 83-305 t/in (32-120 t/cm). Screens stretched to a minimum of 25 newtons are recommended. If using lower tension screens, adjust off contact accordingly. Use just enough squeegee pressure to deposit the ink on the surface of the shirt. A 70, 80 or 70/90/70 durometer sharp squeegee is recommended. All LFP inks are ready to use. They can be extended using K2915 CURABLE REDUCER. Opacity may be affected.
Compliance	
Internationally compliant	
 Non-phthalate 	
 https://www.avientspecialtyinks.com/services/ compliance-support 	
Precautions	
 The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications. 	
Recommended Parameters	



Fabric Types

Cotton



Flash & Cure

Flash: 140-150°F on pre-heated pallets

Cure: 60 seconds at 325°F



Clean Up

Standard plastisol cleaners, press wash, or ink degradant



Mesh

Count: 86-305 t/in Tension: 25n/cm3



Pigment Loading

Not recommended



Health & Safety

Find SDS information here: www.avient.com/resources/safety-datasheets or contact your local CSR



Squeegee

Durometer: 70, 80, or 70/90/70

Profile: Square

Stroke: X1 Stroke, Medium speed

Angle: 5-15%



Additives

K2915 CURABLE REDUCER



Stencil

Standard Emulsion

Off Contact: 1/16" (2mm) or greater

Emulsion Over Mesh: 15-20%



Storage

65 -95° F (18 -35 C) Avoid direct

sunlight.

Use within one year of receipt. Keep container well sealed.



AVIENT SPECIALTY INKS

V1.10 (Modified: 08/18/2023)

2023, Avient Corporation, Avient makes no representations guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or quarantees respecting suitability of either Avient's products or the information for your process or end-use application You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.