

P10843 TXP WHITE LB-TS 200

Printop™ P10843 TXP White LB-TS 200 is a white plastisol textile ink belonging to the TEXIPLAST® Series. It is a product formulated to print on cotton-polyester blended fabrics, where there are problems of migration or transfer of the dye from the fabric to the print. The use of this product reduces the migration problem, it does not eliminate it completely. This product is phthalate free.

HIGHLIGHTS

- /// Reduces dye migration from the substrate to the print
- /// Good opacity on dark fabrics.
- /// Good adhesion
- /// Flexible ink film

PRINTING TIPS

- /// Apply one coat, pre-dry, repeat and cure.
- /// Do not iron on the printed area, do not dry clean.
- /// It is necessary to shake the product before printing.
- /// Always carry out a complete test of finishes, shades, heat setting and washing before mass production.
- /// The user must determine the suitability and applicability of the product for its intended use, checking all the properties described in this data sheet, assuming all the risks and direct and indirect consequences that this use entails.











COMPLIANCE

- /// International compliance
- /// Free of restricted phthalates
- /// <https://specialty-inks.upwardsites.com/services/compliance-support>

PRECAUTIONS

- /// it is recommended that the user perform all appropriate tests to ensure that the desired results are achieved. In some cases, migration testing may take several days. Their effectiveness cannot be guaranteed in all cases. May cause discoloration or ghosting on the reverse side of certain fabrics (pre-testing in this regard is recommended).

RECOMMENDED PARAMETERS

 <p>Fabric Types 100% Polyester, Cotton + Polyester Blend</p>	 <p>Flash & Cure Flash: 3 seconds a 248°F (120°C) Cure: 60 seconds a 320°F(160°C)</p>	 <p>Clean Up Conventional plastisol cleaners.</p>
 <p>Mesh Count: 32 a 61 (t/cm) Tension: 18-25 n/cm3</p>	 <p>Pigment Loading N/A</p>	 <p>Health & Safety SDS: Contact your sales representative.</p>
 <p>Squeegee Durometer: 70 Profile: Rectangle Stroke: x2 stroke, medium speed Angle: 15°</p>	 <p>Additives</p>	<p>2024, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.</p>
 <p>Stencil Direct Off Contact: 1/16" (2mm) Emulsion Over Mesh: 15-20%</p>	 <p>Storage Store in a cool, dry place at 18°C to 35°C (65°F to 95°F). 12 months. Keep container closed to prevent drying and/or contamination.</p>	