

## **EPIC™ RIVAL SPORT™ LC DEFENDER**

WILFLEX<sup>TM</sup> EPIC<sup>TM</sup> RIVAL SPORT<sup>TM</sup> LC DEFENDER is a new technology designed to prevent dye migration on 100% polyester, polyester blends and dye sublimation garments. Use in combination with the RIVAL SPORT<sup>TM</sup> LC Colors and RIVAL SPORT<sup>TM</sup> LC White on fabrics that are prone to bleed more.

#### **HIGHLIGHTS**

Superior opacity

W Low cure, save energy, reduce bleed defects

Lower cure range

- Excellent bleed resistance at a wide temperature range
- Improved printability, creamy viscosity

#### **PRINTING TIPS**

- W Stir inks before printing
- Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- For superior bleed resistance, overprint RIVAL SPORT™ LC DEFENDER with RIVAL SPORT™ LC White and Colors
- RIVAL SPORT™ LC DEFENDER demonstrates improve printability making it ideal for manual and automatic printing
- Print RIVAL SPORT™ LC DEFENDER so that the flashed ink deposit fully covers the underlying fabric, avoid any fabric showing through the under base layer
- Adjust flash cure temperature and dwell time so ink is just dry to touch. Depending on flash unit, a 2 -3 second flash is adequate.
- Curing is a time and temperature process, a lower oven temperature setting with a slower belt speed while maintaining recommended ink cure temperature is always best to protect fabric, control dye migration and reduce energy consumption
- RIVAL SPORT™ LC DEFENDER can be cured between 250°F 300°F (121°C 148°C). Running at the higher end of the temperature range and/or longer dwell times maybe required to achieve proper cure on jobs that contain cotton, high ink deposits or heavy weight garments. Use a setting of 250 on non-stretch, sensitive fabrics, such as polypropylene, Rayon or Denier.

# COMPLIANCE SUSTAINABILITY

#### W Non-phthalate

For individual compliance certifications and conformity statements, please visit: www.avient.com/wilflex-compliance

# **(**

Reduced Energy Use

#### **PRECAUTIONS**

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT SPECIALTY INKS

V1.29 (Modified: 05/15/2024)

#### PRODUCT INFORMATION BULLETIN



#### **RECOMMENDED PARAMETERS**



#### **Fabric Types**

100% polyester, polyester blends, triblends, dye sublimated fabrics



#### Mesh

Count: 86-230 t/in (34-90t/cm) Tension: 25-35 n/cm2



#### Squeegee

Durometer: 60/90/60, 70/90/70, 70 Profile: Square, Sharp Stroke: Hard flood, Fast stroke

Angle: 10-15%



#### **Stencil**

2 over 2

Off Contact: 1/16" (2mm) Emulsion Over Mesh: 15-20%



#### Flash & Cure

Flash: 150° F (66° C)

Cure: 250°F - 300°F(121°C - 148°C)

Entire ink film



#### **Pigment Loading**

N/A



#### Wilflex™ Additives

ASI Viscosity Buster-1% max



#### Storage

65-90°F (18-32°C) Avoid direct sunlight Use within one year of receipt



#### Clean Up

Ink degradant or press wash



## **Health & Safety**

Find SDS information here: www.avient.com/resources/safety-data-sheets or contact your local CSR

2024. Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.