



2558 Infinite FX Luna Clear

2558 Infinite FX Luna Clear is a clear that appears nearly invisible in daylight, but illuminates in the presence of UV blacklight. Use 2558 Infinite FX Luna Clear to create special effects, print secret messages or identify a printer's work by printing hidden licensing data. This ink is an excellent under base that reduces fibrillation and brightens some colors. 2558 Infinite FX Luna Clear will remain bright after numerous washings and may be printed direct or transferred.

HIGHLIGHTS

- Clear when overprinting designs, but illuminates under blacklight conditions
- Suitable for direct print or cold peel transfer application
- Matte finish when printed through high meshes or satin through coarser meshes
- Excellent adhesion to fabrics, stretch properties, and wash durability

PRINTING TIPS

- Stir inks before printing
- Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- For overprint clear - print in last position. Best results when printed over "bright" white or fluorescent colors
- For cold peel transfers, use a coated release paper or polyester film. Print 2558 Infinite FX Luna Clear using 70 duro squeegee and recommended mesh counts, gel and then backed with colors and followed by adhesive. Gel at 212°F (100°C) for 60 sec. Apply transfer with heat press at 300°F (150°C) for 10-12 sec at medium pressure. Verify process.

COMPLIANCE

- Non-phthalate
- For individual compliance certifications and conformity statements, please visit www.avientspecialtyinks.com/services/compliance-support

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



RECOMMENDED PARAMETERS



Fabric Types

100% cotton, cotton blends, some synthetics



Mesh

Count: 110-355 t/in (43-140t/cm)
Tension: 25-35 n/cm2



Squeegee

Durometer: 60/90/60, 60-70
Profile: Square, Sharp
Stroke: Medium flood, Medium stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20%



Flash & Cure

Flash: 220°F (105°C)
Cure: 320°F (160°C)



Pigment Loading

N/A



Additives

N/A



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Dispose unused ink responsibly. Standard plastisol cleaners, press wash, or ink degradant



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR



AVIENT
SPECIALTY
INKS

V1.03 (Modified: 09/26/2024)

2024, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.