



ITOFIX VSRR
Vinyl Sulphone Reactive Dyes

MAGNACOLOURS[®]
IMAGINATION INK[®]

ITOFIX VSRR

Vinyl Sulphone Reactive Dyes



ITOFIX VSRR dyes are a range of dyes based on vinyl sulphone chemistry. Excellent on tone compatibility with good level dyeing capabilities, suitable for exhaust, cold pad batch and continuous application methods.

FASTNESS TEST METHODS

Light Fastness	ISO 105-B02
Wash Fastness	ISO 105-C02
Perspiration Fastness	ISO 105-E02
Water Fastness	ISO 105-E01

SYMBOLS USED IN FASTNESS COLUMNS

C	Staining on cotton
N	Staining on nylon
W	Staining on wool

ITOFIX VSRR DYEING METHOD

Exhaust

Recipe:

x% Dye
0.5g/l ITOQUEST LJ3-12
y g/l Salt
z g/l Alkali

Method:

Heat to 40°C.
Add chemicals and salt, run for 10 minutes.
Heat to 50°C.
Add dyes, run for 30 minutes.
Add alkali over 30 minutes.
(by portions or progressive dosing)
Run for 40 to 60 minutes at 50°C.
Drop liquor and rinse, acid rinse, soap at 100°C.

Cold Pad Batch

Recipe:

x g/l Dye
50g/l ITOPREP MSS
x/5+8 cc/l Caustic Soda 70TW
(x is dye value in g/l)
0.2g/l ITOWET LJ10

Method:

Make dye solution up to 4/5 total volume.
Make chemical solution up to 1/5 total volume.
Mix dye and chemical solutions and pad immediately.
Batch long test for 16-24 hours (Quick test 30 mins at 60°C).
Rinse, acid rinse, soap at 100°C.

ITOFIX VSRR

Vinyl Sulphone Reactive Dyes




ITOFIX		Fastness Properties at 3%										
		Sol	Light	Wash 50°C			Alk Persp			Water		
Dyed at 2%		80°C	1/1	C	N	W	C	N	W	C	N	W
Yellow VSRR		100	4	5	5	5	4/5	4/5	4/5	5	5	5
Orange VSRR		100	4	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
Red VSRR		100	4	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5
Blue VSRR		100	5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5	4/5


Salt and Alkali Table

% Dyestuff	Glaubers Salt	Soda Ash	OR	Soda Ash + Caustic 70tw
<0.3	10	10		-
>0.3 - 0.6	20	10		-
>0.6 - 1.0	30	15		5+1.0
>1.0 - 1.5	40	15		5+1.5
>1.5 - 3	50	20		5+2.0
>3 - 5	80	-		5+3.5
>5	100	-		5+5.0

Specific Gravity of Calcined Glauber's Solutions



Specific Gravity of Common Salt Solutions



REACTIVE DYE RANGES



Application Method	Best Quality	Also Suitable	Cheapest Recipe
EXHAUST			
Warm 50-60°C	ITOFIX VM (pale to medium shades)	ITOFIX VSRR (pale shades)	ITOFIX VS (med-full)
	ITOFIX VMHLF (highest light fastness)	ITOFIX VSRGB (medium to full)	
		ITOFIX VMS (very full shades)	
Hot 80-130°C	ITOFIX CTSNR (pale to full shades)	ITOFIX CT (pale to full shades)	
	ITOREACT (pale to medium shades)		
Cold Pad Batch	ITOFIX VM (pale to medium shades)	ITOFIX VSRR (pale shades)	ITOFIX VS (med-full)
	ITOFIX VMHLF (highest light fastness)	ITOFIX VSRGB (medium to full)	
		ITOFIX VMS (very full shades)	
Pad-Dry-Pad-Steam	ITOFIX VMHLF (highest light fastness)	ITOFIX VSRR (pale shades)	ITOFIX VS
	ITOFIX P (medium to full shades)	ITOFIX VSRGB (medium to full)	
		ITOFIX VMS (very full shades)	
Pad - Dry - Steam	ITOFIX P (pale to full shades)	ITOFIX VSRR (pale shades)	ITOFIX VS
		ITOFIX VSRGB (medium to full)	
		ITOFIX VMS (very full shades)	
Pad - Steam		ITOFIX VM (pale to medium)	ITOFIX VS
Pad-Dry-Thermofix	ITOFIX P (pale to full shades)	ITOFIX VSRGB (medium to full)	ITOFIX VS
	ITOFIX VMHLF (highest light fastness)	ITOFIX VMS (very full shades)	
E Control	ITOFIX P (pale to full shades)	ITOFIX VSRR (pale shades)	ITOFIX VS
	ITOFIX VMHLF (highest light fastness)	ITOFIX VSRGB (medium to full)	
Printing	ITOFIX P (pale to full shades)		ITOFIX VS

IMPORTANT - In producing these dye pattern cards, MagnaColours Ltd. has used reasonable endeavours to provide information that is accurate and reliable and the documents detail the reasonable conclusions that can be reached on the basis of the information available to MagnaColours. The dye pattern cards are provided to give no more than an indication of the nature of the products offered upon their application and, for the avoidance of doubt, are in no way intended to nor will amount to a sale by sample. You should verify the suitability of the product for specific applications, and the use of the information in whole or in part by you or by any third party working with or for you for any reason will be entirely at your risk.

All implied warranties and conditions are excluded, to the maximum extent permitted by law. For the avoidance of doubt, MagnaColours cannot be held responsible for any action resulting from the use of the information and, to the fullest extent permitted by law, MagnaColours excludes all liability or whatever nature (whether direct, indirect, consequential, special or otherwise) with regards to or arising from such use.

Some products contained herein may not be available, permitted or lawful in your country or territory and a reference to a particular product does not imply that MagnaColours intends to make such products or services available in such countries and territories. Please check availability of products within your territory with your local supplier.

MAGNACOLOURS[®]
IMAGINATION INK[™]



MagnaColours Limited
Upper Cliffe Road,
Dodworth Business Park,
Barnsley, S75 3SP, UK

T: 00 44 (0) 1226 731751
F: 00 44 (0) 1226 731752
E: info@magnacolours.com
www.magnacolours.com

Company registered in
England No. 01378495,
VAT No. GB 997 3172 70

