



## MagnaPrint® Bling Range

### Ready to use metallic printing pastes

MagnaPrint® Bling is a ready to use metallic print paste that has excellent shine and elasticity. The paste may be pigmented with MagnaPrint® Eco Pigments to achieve different colours such as Bling Gold & Bronze. Recipes are available upon request.

### Application

MagnaPrint® Bling should be printed through a 32 - 61 (86 - 156) mesh screen with rectangular profile squeegees. As the particle size is 10 - 60 micron this should be considered when selecting screen mesh.

When printing as part of a multicoloured design print the MagnaPrint® Bling as the last screen to avoid pick up.

After printing the garment/panel should be cured, ideally for 2½ - 3 minutes at 165°C (330°F).

### SPECIFICATION



#### FABRIC TYPES

Cotton / Poly Cotton blends



#### MESH

32 - 61T (86 - 156)



#### SQUEEGEE

Medium 65° Shore  
Rectangular



#### STENCIL

Water resistant emulsion



#### CURE TEMPERATURE

2½ - 3 minutes at 165°C  
(330°F)



#### PIGMENT LOADING

Up to 6% MagnaPrint® Eco  
Pigments



#### ADDITIVES

Retardant Gel, Crosslinker 100,  
Softener TS Conc



#### STORAGE

In cool place properly closed:  
>5°C (40°F) <25°C (77°F)



#### HEALTH & SAFETY

MSDS available upon  
request



#### CLEAN UP

Wash off screen using water  
and mild detergent

All information is given in good faith but without warranty. They do not release you from testing our products as to their suitability for the intended processes and uses.