



MagnaPrint® Ecofix XL

Fastness improver for high pigment loadings

MagnaPrint® Ecofix XL is a crosslinking agent, specifically designed to improve wash and rub-fastness. MagnaPrint® Ecofix XL is compatible with all MagnaPrint® bases.

Application

Add up to 5% MagnaPrint® Ecofix XL, mix well and cure at 140°C (284°F) for 2 mins or 165°C (330°F) for 1.5 minutes

SPECIFICATION



CURE TEMPERATURE

2mins at 140°C (284°F) or
1½ mins at 165°C (330°F)



STORAGE

In cool place properly closed:
>5°C (40°F) <25°C (77°F)



HEALTH & SAFETY

MSDS available upon
request



CLEAN UP

Wash off screen using water
and mild detergent

Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

