



MagnaPrint® High Gloss

Glossy ready to use water-based printing paste

MagnaPrint® High Gloss is a ready to use water-based printing paste and can be used to obtain glossy effects on coloured substrates.

MagnaPrint® High Gloss can be coloured with MagnaPrint® Pigments, pearls or glitters to achieve interesting visual effects.

Application

Printing is best undertaken using 32 - 43 (86 - 110) mesh screens with rectangular squeegees.

When printing as part of a multicoloured design, print the MagnaPrint® High Gloss as the last screen to avoid pick up.

After printing, curing and raising of the print should be carried out at a maximum temperature of 150°C (305°F) for 3 minutes.

Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as 'typical' or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

SPECIFICATION



FABRIC TYPES

Cotton / Poly Cotton blends



MESH

32 - 43T (86 - 110)



SQUEEGEE

Medium 65° Shore
Rectangular



STENCIL

Water resistant emulsion



CURE TEMPERATURE

3 minutes at 150°C (305°F)



PIGMENT LOADING

Up to 6% MagnaPrint® Eco Pigments



ADDITIVES

Retardant Gel, Crosslinker 100



STORAGE

In cool place properly closed:
>5°C (40°F) <25°C (77°F)



HEALTH & SAFETY

MSDS available upon request



CLEAN UP

Wash off screen using water and mild detergent